

# DINITROL 4010 Corroheat

## Resistant corrosion inhibitor for surface and engine protection

DINITROL 4010 Corroheat is versatile and can be used in both open and closed areas. The product penetrates like a cavity wax. It can also be used in electrical systems to avoid galvanic corrosion and other negative influences such as moisture.

» High mechanical resistance

» High temperature resistance

» Excellent adhesion

» Long-term protection



### Equipment

**DINITROL Spray Tool UBS 1-P**  
Art. No. 1700700

**DINITROL Spray Tool UBS/HR GSI**  
Art. No. 1701900

**DINITROL Pump unit for 20 L Pails**  
Art. No. 1705100

**DINITROL Airless Pump 1:26**  
Art. No. 1705900

### DINITROL 4010 Corroheat

Art. No.	Size	Package	Color
11250	500 ml	Can	Trans. beige
11249	1 L	Can	Trans. beige
11423	10 L	Pail	Trans. beige
11247	20 L	Pail	Trans. beige
11246	60 L	Drum	Trans. beige
11245	208 L	Drum	Trans. beige

a brand of

**DINOL**

**DINOL GmbH** Pyrmonter Straße 76, D-32676 Lügde, Germany  
Tel. +49 (0) 5281-98 2 98-0, Fax +49 (0) 5281-98 2 98-60, [www.dinol.com](http://www.dinol.com)

09.2022

All data and recommendations are the result of careful tests by our laboratory. They only can be considered as recommendation which corresponds to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the misuse of our products. Therefore, a contractual legal relationship is not justified, and there are no secondary obligations arising from any purchase contracts.

# DINITROL 4010 Corroheat

## Technical Details

### Product description

DINITROL 4010 Corroheat leaves a hard, transparent film that is resistant to both alkali and acids and is heat resistant up to a temperature of 200°C. It has a tack-free and clean film which facilitates a visual inspection of metal surfaces, reading of labels and numbers etc.

### Applications

The adhesion and flexibility on rubber and plastic parts at both low and high temperatures are very good. Appropriate parts to be treated with DINITROL 4010 Corroheat are engine compartments, engines and other parts which have to withstand high temperatures.

### Method of use

DINITROL 4010 Corroheat should be applied on a clean, dry surface. High or low pressure equipment can be used, airless or airmix. Application temperature between 15 – 30°C. Product hardness, flexibility and adhesion increases at higher drying temperatures.

### Pre-treatment Substrates

Surfaces shall be dry, clean and free from corrosion.

### Over-Coating

Normally not to be overpainted. For additional information, please consult DINOL GmbH.

### Storage

The product should be stored at 15 – 30°C and the shelf life is then 2 years in unopened original packages.

## Technical Data

Colour	transparent beige
Type of film	hard, waxy
Density at 23°C	890 kg/m <sup>3</sup>
Viscosity at 23°C, DIN 4	25 seconds
Dry matter content	47% by weight
Aromatic part in the solvent	0,5 %
Recommended film thickness wet	120 µm
Recommended film thickness dry	40 µm
Drying time	120 µm wet, 1 h with optimal ventilation 120 µm wet, 4-6 hours at RT 23°C 50% RH
Low temperature adhesion	-30°C
Effect on car paint	none
Removability within 3 months	Hydrocarbon solvents
Heat resistance	
Short-term	200°C
Long-term	160°C
Salt spray test (drying 24 h, 80°C)	240 hrs 40 microns dry 500 hrs 80 microns dry
Available in	500 ml Spray Can / 1 L Can / 10 L Canister / 20 L Pail / 60 L Drum / 208 L Drum

**For all relevant safety advices please read the material safety data sheet or the packaging label.**