

DINITROL 958

Waterbased Stonechip Protection

DINITROL 958 is a waterbased and acrylic based stonechip protection. It forms a black, hard film that offers very good protection against mechanical influence. It is, after drying, overpaintable.

» Water-based

» OEM references

» Quick drying, black, flexible film

» Environmentally friendly, solvent-free

» Can be coated



Equipment

DINITROL Spray Tool HS 1-P
Art. No. 1700500

DINITROL Spray Tool UBS/HR GSI
Art. No. 1701900

DINITROL Cavity Nozzle Set
Art. No. 1702000

DINITROL Pump Unit for 20 L Pails
Art. No. 1705100

DINITROL Airless Pump 1:26
Art. No. 1705900

DINITROL 958

Art. No.	Size	Package	Color
11545	1 L	Can	Black
11196	20 L	Pail	Black
11398	208 L	Drum	Black

a brand of



DINOL GmbH Pyrmonter Straße 76, D-32676 Lügde, Germany
Tel. +49 (0) 5281-98 2 98-0, Fax +49 (0) 5281-98 2 98-60, www.dinol.com

09.2022

All data and recommendations are the result of careful tests by our laboratory. They only can be considered as recommendation which corresponds to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the misuse of our products. Therefore, a contractual legal relationship is not justified, and there are no secondary obligations arising from any purchase contracts.

DINITROL 958

Technical Details

Product description

DINITROL 958 is quick drying water based stone chip protection product. DINITROL 958 provides a black elastic film, which efficiently protects the vehicle body from stone chips and road salt. DINITROL 958 is environmental friendly as it is free from solvent.

Applications

DINITROL 958 is designed for treatment of cars, buses, trucks and other vehicles, on line application as well as in the aftermarket. The product is designed to protect the most exposed parts such as doorsills, spoilers, bumpers, wheel arches, and edges. DINITROL 958 can after drying be over painted with most car lacquers.

Method of use

DINITROL 958 can either be applied with brush, low or high pressure equipment. The spraying is recommended airless with a product temperature of +15°C – +30°C.

Pre-treatment Substrates

Surfaces to be applied shall be dry, clean and free from corrosion.

Over-Coating / 2-Layer-Application

DINITROL 958 can be overpainted with most common paints. It is recommended to make a test application to make sure it is working properly. For additional information please consult DINOL.

Storage

The storage temperature are 5 – 35°C and shelf life 12 months. Cool and moisture free stored the product is tenable for a maximum of 1 year in the unopened original packaging.

Technical Data

Colour	black
Type of film	elastic
Density	1300 kg/m ³
Viscosity at 23°C	7500 mPas
Dry matter content	63% by weight
Recommended film thickness wet	500 – 700 µm
Recommended film thickness dry	200 – 300 µm
Drying time	45 min under optimal conditions
Effect on car paint	none
Removability	Water and alkaline cleaner
Heat resistance	> 100°C
Salt spray resistance at 300 µm	> 1000 h
Shelf life	12 months
Available in	1 L Can / 20 L Pail / 208 L Drum

For all relevant safety advices please read the material safety data sheet or the packaging label.